

DUPLI-COLOR CAR`S WHEEL PAINT**Technical Information**

Gives a decorative shine to rims. Durable, high-pigmented protective coating for steel and alloy rims.

Ord.-no: 385902, 385919, 693823

Quality & properties

High-grade, quick-drying nitro-combi lacquer
Good flow, smooth surface
Weather-resistant, light-proof and non-yellowing
Limited fuel-resistant
Good colour and gloss retention
Hard surface, abrasion-resistant

Physical & chemical data

Base: Nitrocombi resin
Colourname:

- gold
- silver

Degree of gloss: mat GU
Efficiency:

- 400 ML – 0.8 m²
- 600 ML – 1.2 m²

Dry to touch: 30 min
Dust dry: 15 min
Surfaces: metal, wood, ceramics, stone, carton and others
Minimum Working Temperature: 10 °C
Maximum Working Temperature: 25 °C
Flash point: n.a.
Storage stability: 10 y
Content:

- 400 ML
- 600 ML

How to use

Preparation of the ground:

Carefully clean rims from dirt, fat and brake-dust.

Treat existing pore rust with presto Deruster.

The ground has to be sanded, clean, dry and fat-free.

Mask off the rim edges with masking tape.

Use paper to protect surrounding area from spray-dust.

Prime with CAR's Primer.

After drying, slightly sand (sanding paper grain P600)

Lacquering:

Before use, shake the can vigorously for 3 minutes.

Test spray to check colour-matching.

Spray several thin coats in 3 - 5 minute intervals from a distance of approx. 25 cm.

After 60 minutes drying time, coat with CAR's Clear Lacquer to protect the metal pigments in the lacquer.

Do not spray over synthetic paints!

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.