

DUPLI-COLOR COLOR SPECIAL CERAMIC SPRAY

Technical Information



To repair defective white enamel surfaces, such as water basins, kitchen sinks, bath tubs, refrigerators, boilers etc. For hard, durable surfaces.

Ord.-no: 652028

Quality & properties

- High-grade acrylic quality
- For white glossy enamel surfaces
- Hard, durable surface
- Very good coverage
- Excellent adhesion
- Good flow, smooth surface
- Quick-drying
- Scratch-, shock- and impact-resistant

Physical & chemical data

- Base: Acrylic resin
- Colourname: white
- Degree of gloss: gloss GU
- Efficiency: 400 ML – 0.8 - 1.0 m²
- Dust dry: 5 min
- Completely dry: 2 h
- Overcoatable: 1 h
- Surfaces: metal, wood, glass, ceramics, polystyrene, eternite, concrete, stone, paper, carton, hard plastics, flowers etc
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 25 °C
- Flash point: n.a.
- Storage stability: 10 y
- Content: 400 ML

How to use

- Remove loose parts, rust and dirt.
- The surface has to be clean, dry and free of fat.
- Slightly sand the damaged area and a small part of the surrounding surface.
- Remove abrasive dust.
- The aerosol can should have room temperature.
- Before use shake the can vigorously for 2-3 minutes.
- Test colour of spray and compatibility of the lacquer at an invisible spot.
- Spray several thin cross-coats from a distance of approx. 25 cm.
- Do not spray over synthetic paints!

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 21, 2025 – This release replaces all eventually earlier issued versions.