

DUPLI-COLOR 1 K CORROSION PROTECTION AUTOMOTIVE

Technical Information



Protects metals, such as iron and steel sheet, reliably from corrosion. The high quality Corrosion Protection Primer dries very fast, has a good adhesion and covers well. An ideal primer for even and glossy surfaces with good adhesive properties.

Ord.-no: 652042, 652059

Quality & properties

Combination of special paint resins
Excellent protection to corrosion due to special rust-protective additives
Promotes best adherence of the top coat on the object
Very good coverage and adhesion
Suitable for indoors and outdoors applications
Quick-drying
Good flow, smooth surface
Grants even, glossy, well-adhering paint surfaces

Physical & chemical data

Base: Special resin
Colourname: redbrown
Degree of gloss: mat GU
Efficiency:
◦ 150 ML – 0.3 - 0.4 m²
◦ 400 ML – 0.8 - 1.0 m²
Dry to touch: 30 min
Dust dry: 10 min
Completely dry: 24 h
Overcoatable: 1-2 h
Surfaces: sheet steel, motor cycle parts, iron fences, sheet metal covers, etc.
Minimum Working Temperature: 10 °C
Maximum Working Temperature: 25 °C
Flash point: n.a.
Storage stability: 10 y
Content:
◦ 150 ML
◦ 400 ML

How to use

Carefully remove loose flakes of old paint and rust, then sand and clean from abrasive dust.
The surface has to be clean, dry and free from fat.
Before use, shake can for 2 minutes, then test spray.
Spray in 2 minute intervals several thin coats.
Spray from a distance of approx. 25 cm.
Coatable with synthetic or acrylic lacquers; do not spray over synthetic paints!

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.