

DUPLI-COLOR COLOR SPECIAL ZINC-ALU SPRAY

Technical Information



Zinc Alu Primer for zinc-plated parts and surfaces, which have been damaged by welding, sanding, drilling, transportation etc., and which have to be repaired or adapted to colour shade.

Also suitable as excellent corrosion protection for metal surfaces and black iron metals. Suitable for only a limited extent on aluminium. Overpaintable with air-drying acrylic, NC or synthetic lacquers.

Heat-resistant up to 300°C. Electrically conductive.

Ord.-no: 652257

Quality & properties

- Rust-protecting
- Heat-resistant up to 300°C
- Resistant to changing temperatures
- Good flow
- Coatable with air-drying acrylic, nitro-combi and synthetic lacquers

Physical & chemical data

- Base: 1K Epoxy resin
- Colourname: grey
- Degree of gloss: mat GU
- Efficiency: 400 ML – 1.0 - 1.5 m²
- Dry to touch: 60 min
- Dust dry: 15 min
- Completely dry: 12 h
- Surfaces: for all iron metals, such as car bodies, exhaust systems, gates, machines, metal housings, metal fittings, fences etc
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 25 °C
- Flash point: n.a.
- Storage stability: 10 y
- Content: 400 ML

How to use

- The ground has to be clean, dry and free from rust and fat.
- Shake can vigorously for approx. 2 minutes.
- Test spray at an invisible spot.
- Apply several covering coats.
- Spray from a distance of approx. 25 cm.
- Can be coated with itself. It is possible before and to apply a top coat.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 21, 2025 – This release replaces all eventually earlier issued versions.