

DUPLI-COLOR CAR'S CLEAR COAT

Technical Information



Glossy finish for DUPLI-COLOR spray paints on acrylic or nitrocombi basis, such as Wheel-, Neon- and other non-metallic car paint sprays. Adds gloss and protection to all rallye paintings.

Ord.-no: 385858, 693830, 720352, 100007

Quality & properties

- High-grade acrylic quality
- Excellent adhesion
- Good flow, smooth surface
- Excellent gloss stability
- Hard surface, good elasticity
- Quick-drying
- Light-proof, UV-proof (non-yellowing)
- Resistant to weathering, dirt-repellent
- Scratch-, shock- and impact-resistant
- After curing resistant to water, diluted acids and bases
- Limited fuel-resistant

Physical & chemical data

- Base: Acrylic resin
- Colourname: transparent
- Degree of gloss: gloss GU
- Efficiency:
 - 400 ML – 1,5 m²
 - 600 ML – 2,3 m²
 - 400 ML – 1.0 - 1.5 m²
 - 600 ML – 6 m²
- Dry to touch: 50 min
- Dust dry: 10 min
- Completely dry: 24 h
- Minimum Working Temperature:
 - 10 °C
 - 10
- Maximum Working Temperature:
 - 25 °C
 - 25
- Flash point: n.a.
- Temperature Resistance: 80 °C
- Storage stability: 10 y
- Content:
 - 400 ML
 - 600 ML

How to use

The previous paint coat has to dry for at least 30 minutes (observe the instructions on the previous paint Spray can).
Before use, shake the clear lacquer can for 3 minutes.
Spray from a distance of 25 cm several thin coats.
Remove spray dust after 24 hours drying time with presto Polishing Paste
Do not spray over surfaces which are painted with synthetic resin lacquer!

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.