

## DUPLI-COLOR profi White Lacquer

## Technical Information



Universally applicable top coat for brilliant white. For painting furniture, doors, windows and repairs to walls. Can be used on metal, wood, glass, stone, ceramic, cardboard and paintable plastics.

**Ord.-no:** 289613, 289620

### Quality & properties

High-grade acrylic quality  
Quick drying; hard surface  
Very good coverage  
Excellent adhesion on many materials  
Good flow, smooth surface  
Suitable for indoors and outdoors applications  
Weather-resistant, light-proof, UV-resistant

### Physical & chemical data

Base: Acrylic resin  
Colourname: white  
Degree of gloss:  
◦ gloss GU  
◦ satin mat GU  
Efficiency: 400 ML – 1.0 m<sup>2</sup>  
Dry to touch: 30 min  
Dust dry: 10 min  
Completely dry: 2 h  
Overcoatable: 30 min  
Surfaces: metal, wood, glass, stone, ceramics, carton and on paintable plastics  
Minimum Working Temperature: 10 °C  
Maximum Working Temperature: 25 °C  
Flash point: n.a.  
Storage stability: 10 y  
Content: 400 ML

---

### How to use

Remove rust and dirt.  
The surface has to be clean, dry and free from fat.  
If necessary, apply a primer.  
Cover areas not to be painted.  
Before use, shake the can for 2-3 minutes.  
Test spray to check colour-matching and compatibility.  
Spray: apply from a distance of approx. 25 cm several thin cross-coats.  
Do not apply on synthetic paints!  
Before application on paintable plastics use DUPLI-COLOR Plastic Primer

### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

### Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

**As of May 21, 2025** – This release replaces all eventually earlier issued versions.