

DUPLI-COLOR COLOR SPECIAL METAL

Technical Information



Decorative bronze gloss in different shades like silver and gold. For handicraft works on wood, metal, glass, cardboard etc.

Ord.-no: 585067, 585074, 640599, 683824, 640582, 683817, 685002

Quality & properties

High-grade synthetic quality
Long-term high coverage and filling power
Excellent adhesion
Good flow, smooth surface
Quick-drying
Suitable for use on indoor objects
Limited resistance to abrasion and to weathering

Physical & chemical data

Base: Alkyd resin
Colourname:
◦ silver
◦ gold
◦ antique gold
Degree of gloss: semi gloss GU
Efficiency:
◦ 400 ML – 1.0 m²
◦ 150 ML – 0.4 m²
◦ 200 ML – 0.5 m²
Dry to touch: 60 min
Dust dry: 10 min
Completely dry: 24 h
Overcoatable: 2 h
Surfaces: wood, metal, glass, cardboard, plants etc
Minimum Working Temperature: 10 °C
Maximum Working Temperature: 25 °C
Flash point: n.a.
Storage stability: 10 y
Content:
◦ 400 ML
◦ 150 ML
◦ 200 ML

How to use

The ground has to be clean, dry and free of fat.
Absorbant surfaces should be primed with DUPLI-COLOR Universal Primer.
Mask off areas not to be painted.
Shake the can vigorously for approx. 3 minutes.
Test spray at an invisible spot to check colour and compatibility.
Spray several thin coats from a distance of approx. 25 cm.
Due to technical reasons it is not possible to conserve the excellent high gloss. A coat of clear lacquer would dissolve the effect lacquer. Just renew the gloss by applying a new coat of bronze spray.
Do not coat with acrylic lacquer - not even after curing

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.