

**DUPLI-COLOR PLASTIC PRIMER
AUTOMOTIVE****Technical Information**

Bonding agent for subsequent painting of plastic parts, suitable for car parts, garden furniture or other objects made of hard plastic. Can be used on: Polyurethane (PUR), polystyrene (PS), polyamide (PA), ethylene propylene diene monomer rubber (EPDM), acrylonitrile butadiene styrene plastic (ABS) and glass fibre reinforced plastic (GfK). Before application, we recommend to wet-sand plastic parts with presto wet-sandpaper P600 art.no. 135934 and to clean them with DUPLI-COLOR Plastic Cleaner art.no. 386343.

Ord.-no: 609367, 327292

Quality & properties

Solvent-based product with special adhesion-promoting additives
Quick-drying
Suitable for indoors and outdoors applications
Good resistance to outside influences
Good flow, smooth surface

Physical & chemical data

Base:
◦ Acrylate copolymers
◦ Special resin
Colourname: transparent
Efficiency: 150 ML – 5.0-6.0 m²
Dust dry:
◦ 10 min
◦ 15 min
Completely dry: 24 h
Overcoatable: 15 min
Surfaces: car parts, garden furniture and other objects of coatable hard plastics
Minimum Working Temperature: 10 °C
Maximum Working Temperature: 25 °C
Flash point: n.a.
Storage stability: 10 y
Content:
◦ 150 ML
◦ 400 ML

How to use

Clean surface from dirt, fat and silicone.
Evtl. sand with sandpaper grain 600.
Remove abrasive dust.
Before use, shake can for 3 minutes.
Apply max. 2 thin layers.
Spray from a distance of approx. 25 cm.
After drying (approx. 15 minutes) coatable with acrylic, synthetic or nitro-combi lacquers.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.