

DUPLI-COLOR Alkyton Synthetic Thinner

Ord.-no.: 387555

Technical Information



Suitable thinner for Alkyton and other synthetic brush paints

Quality & properties

- Thinner for all Alkyton lacquers as well as other solvent-containing synthetic or chlorinated rubber paints
- Slowly evaporating thinner for perfect paint coats
- Excellent cleaning power: removes paint splatters and colour stains
- Do not use on synthetic material and painted surfaces

Physical & chemical data

- Colourname: transparent
- Smell: Characteristic
- Vapour pressure: 6,7-8,2/20 bar
- Flash point: 26 °C
- Relative density: 0.798 g/cm³
- Storage stability: 5 y
- Content: 500 ML

How to use

- As cleaner: to clean up tools, paint splatters etc.
- As thinner for Alkyton lacquers we recommend for application with: Brush: Up to 10 vol. % synthetic thinner; use natural bristles, long hair brushes. Roller: Up to 10 vol % synthetic thinner; use short nap, polyamide (Perlon) 6 – 12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness. Spraygun: 10 - 25 vol. %: synthetic thinner Gravity cup and pressure cup. Tip size: 1,0 - 1,5 mm. Atomising pressure: 2 - 4 bar.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +49 (0) 62 66 75-266 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of August 18, 2022 – This release replaces all eventually earlier issued versions.